



12/17/99

PTO/SB/06 (12/97)
 Approved for use through 09/30/00. OMB 0861-0032
 Patent and Trademark Office: U.S. DEPARTMENT OF COMMERCE

UTILITY PATENT APPLICATION TRANSMITTAL

(Only for new nonprovisional applications under 37 CFR 1.63(b))


Attorney Docket No.
00202/K-210(Kanpe)/YE F99046

Total Pages: 24

First Named Inventor or Application Identifier

Tadashi WATANABE et al.

Express Mail Label No.:



12/17/99

APPLICATION ELEMENTS

See MPEP chapter 600 concerning utility patent application contents.

ADDRESS TO: Assistant Commissioner for Patents
 Box Patent Application
 Washington, D.C. 20231

1. ☐ Fee Transmittal Form
 (Submit an original, and a duplicate for fee processing)

6. Microfiche Computer Program (Appendix)

2. ☐ Specification [Total Pages -25]
 (preferred arrangement set forth below)

7. ☐ Nucleotide and/or Amino Acid Sequence Submission
 (if applicable, all necessary)

- Descriptive title of the Invention
- Cross References to Related Applications
- Statement Regarding Fed sponsored R & D
- Reference to Microfiche Appendix
- Background of the Invention
- Brief Summary of the Invention
- Brief Description of the Drawings (if filed)
- Detailed Description
- Claim(s)
- Abstract of the Disclosure

- a. ☐ Computer Readable Copy
- b. ☐ Paper Copy (identical to computer copy)
- c. ☐ Statement verifying identity of above copies

ACCOMPANYING APPLICATION PARTS

3. ☐ Drawing(s) (35 USC 113) [Total sheets -]

8. ☒ Assignment Papers (cover sheet & document(s))

4. ☒ Oath or Declaration [Total Pages - 3]

9. ☐ 37 CFR 3.73(b) Statement ☐ Power of Attorney
 (when there is an assignee)

a.1. ☒ Newly executed (original or copy)

10. ☐ English Translation Document (if applicable)

a.2. ☐ Unexecuted

11. ☐ Information Disclosure Statement (IDS)/PTO-1449
☐ Copies of IDS Citations

b. ☐ Copy from a prior application (37 CFR 1.63(d))
 (for continuation/divisional with Box 17 completed)

12. ☐ Preliminary Amendment

[Note Box 5 below]

13. ☒ Return Receipt Postcard (MPEP 503)

i. ☐ DELETION OF INVENTOR(S)

Signed statement attached deleting inventor(s)
 named in the prior application, see 37 CFR
 1.63(d)(2) and 1.33(b).

(Should be specifically itemized)

14. ☐ Small Entity Statement(s)

5. ☐ Incorporation By Reference

(usable if Box 4b is checked)

The entire disclosure of the prior application, from which
 a copy of the oath or declaration is supplied under Box
 4b, is considered as being part of the disclosure of the
 accompanying application and is hereby incorporated by
 reference therein.

☐ Statement filed in prior application, Status still proper and desired

15. ☐ Certified Copy of Priority Document(s)

(if foreign priority is claimed)

16. ☐ Other

17. If a CONTINUING APPLICATION, check appropriate box and supply the requisite information:

☐ Continuation ☐ Divisional ☐ Continuation-in-part (CIP) of prior Application No.

18. CORRESPONDENCE ADDRESS

WENDEROTH, LIND & PONACK
 2033 "K" Street, N.W.
 Suite 800
 Washington, D.C. 20006
 Phone:(202) 721-8200
 Fax:(202) 721-8250

December 17, 1999

COATED METAL PLATE

BACKGROUND OF THE INVENTION

5 1. Field of the Invention

The present invention relates to a metal plate comprising a conductive plastic coated film and an electrodeposition coated film which are laminated and coated at least on one surface thereof, which is particularly useful as an outer plate part for car bodies and
10 electrical appliances.

2. Description of the Related Art

It is widely carried out to apply electrodeposition paint as a primer on a metal plate and then apply intermediate paint and topcoat paint to form a composite coated film, but there is the defect
15 that if an impact given by allowing small stone to strike is exerted on this composite coated film, a coated film at a part thereof is liable to be locally peeled off. Further, at least three kinds of paints have to be applied in order to form this composite coated film, and labor saving at these coating steps and a reduction in carbon dioxide are
20 strongly requested.

SUMMARY OF THE INVENTION

Investigations repeated by the present inventors in order to solve such problems as described above in a metal plate coated
25 with a composite coated film have resulted in finding that the problems described above can be solved at a stroke by laminating and coating a conductive plastic coated film and an electrodeposition coated film on a metal plate, and they have come to complete the present invention.

30 Thus, according to the present invention, provided is a coated metal plate characterized by comprising a conductive plastic

coated film and an electrodeposition coated film which are laminated at least on one surface of a metal plate.

The coated metal plate of the present invention shall be explained below in detail.

5

DESCRIPTION OF SPECIFIC EMBODIMENTS

A metal plate used for preparing the coated metal plate of the present invention includes, for example, metal plates of iron, steel, stainless steel, aluminum, copper and alloys containing these
10 metals, and metal plates obtained by plating the surfaces thereof with zinc, zinc/nickel and aluminum, and they can be used in the form of a coil or a cut plate. The metal plates have suitably a thickness falling in a range of usually 0.3 to 2.0 mm, particularly 0.5 to 1.0 mm. The surfaces of these metal plates are preferably subjected
15 in advance to suitable preliminary treatment such as polishing treatment, degreasing treatment and phosphate treatment in order to elevate an adhesive property with a plastic layer and an anticorrosive property.

Plastics used for coating these metal plates shall not
20 specifically be restricted, and there can be used, for example, known optional thermoplastic resins including polyolefin resins such as polyethylene and polypropylene, polyester resins such as polyethylene terephthalate (PET), polycarbonate resins, epoxy resins, vinyl acetate resins, vinyl chloride resins, fluorine-containing resins,
25 polyvinyl acetal resins, polyvinyl alcohol resins, polyamide resins such as nylon, polyphenylene oxide, acetal resins, ABS resins, polystyrene resins, acryl resins, polyurethane resins, phenol resins, polyether resins, polyetherimide resins, and fiber base resins. These resins can suitably be blended with color pigments and extender
30 pigments.

The metal plate can be coated with the plastic film by

known methods. It can be coated, for example, by such methods that a film-shaped or sheet-shaped plastic molded by extrusion molding, injection molding, calendar molding and compression molding is adhered on a metal plate; a plastic molten by heating is extruded
5 into a film or sheet, and it is adhered on a metal plate by pressing; and a solution or a dispersion of the resins described above is coated on a metal plate. The plastic film is coated on the surface of the metal plate positioned at least on the outside of a product for which the coated metal plate is used and can be coated, if desired, on both
10 surfaces including a back surface.

The plastic coated films thus formed on the metal plate have a thickness falling suitably in a range of usually 1 to 100 μm , particularly 3 to 75 μm and more particularly 5 to 50 μm . Further, these plastic films can be subjected on the surfaces thereof to treat-
15 ment such as corona discharge treatment, plasma treatment and flame treatment before or after coated on the metal plate.

In sticking a film-shaped or sheet-shaped plastic on the metal plate to coat the metal plate with the plastic, an adhesive is preferably applied in advance on the surface of the metal plate
20 and/or the plastic film or sheet in order to enhance an adhesive property between both. Such adhesive includes, for example, thermosetting or thermoplastic adhesives containing at least one resin selected from bisphenol type epoxy resins, resol type epoxy resins, acryl resins, aminoplast resins, polyester resins, urethane resins and
25 polysiloxane resins and, if necessary, a curing agent. Further, there can also be used as the adhesive, triazinethiol base compounds such as 2,4,6-trimercapto-s-triazine, 2-dibutylamino-4,6-dimercapto-s-triazine, 2,4,6-trimercapto-s-triazine monosodium salt and 2,4,6-trimercapto-s-triazine trisodium salt.

30 In the present invention, this plastic coated film has to be provided with a conductivity, and to be specific, it can be provided by

such a method as (a) dispersing and incorporating a conductive substance into the inside of the plastic coated film or (b) forming a film of a conductive substance on the surface of the plastic coated film.

5 In the method (a) described above, the conductive substance which can be dispersed and incorporated into the inside of the plastic coated film includes, for example, palladium, copper, aluminum, iron, nickel, carbon black, carbon fiber and graphite, and the plastic film can be provided with a conductivity by mixing and
10 dispersing a powder of at least one conductive substance selected from them into the plastics described above. The powder of these conductive substances can have an average particle diameter falling in a range of usually 0.1 to 10 μm , preferably 0.1 to 5 μm . The conductive substance in the inside of the plastic coated film can have
15 such content that the resulting conductive plastic film has a volume specific resistance value of $10^3 \Omega \cdot \text{cm}$ or less, preferably $10^2 \Omega \cdot \text{cm}$ or less and more preferably 50 $\Omega \cdot \text{cm}$ or less, wherein the volume specific resistance value is determined according to JIS K6911-1955.

 In the method (b) described above, a continuous film of a
20 conductive substance is formed on the surface of the plastic coated film to form a conductive layer. To be specific, a continuous film of a conductive metal such as gold (Au), palladium (Pd) and aluminum (Al) or a semiconductor such as metal oxides of indium (In), titanium (Ti), cadmium and tin and copper iodide can be formed on the surface
25 of the plastic coated film by a method such as vacuum deposition, sputtering, spray and electroless plating. This conductive film has a film thickness falling preferably in a range of usually 1 μm or less, particularly 0.1 to 0.01 μm . The conductive plastic film obtained by this method has a surface resistance value of 100 Ω/\square or less,
30 particularly 50 Ω/\square or less and more particularly 10 Ω/\square or less. In this method (b), the plastic film itself on which the conductive

layer is formed may be either non-conductive or conductive. The surface resistance value is determined according to JIS K6911-1955.

The plastic coated film is coated on one surface or both surfaces of the metal plate. The plastic coated film can be provided
5 with a conductivity on one surface thereof in the former case and on either one or both surfaces of the plastic coated films laminated on both surfaces of the metal plate in the latter case. In the present invention, the plastic coated film surface provided with a conductivity is preferably disposed oppositely to the surface of a product for
10 which this is intended to be used.

The coated metal plate of the present invention can be produced by laminating an electrodeposition coated film on the surface of the above conductive plastic coated film of the metal plate (hereinafter called "conductive coated metal plate") coated with the
15 conductive plastic coated films in the manner described above. To be specific, the conductive coated metal plate is cut to an intended shape and size, molded and, if necessary, joined to prepare a molded article having an intended form, and then the surface of the conductive plastic coated film in the above molded article is coated by
20 electrodeposition.

The coated metal plate provided by the present invention in which the conductive plastic coated film and the deposition coated film are laminated at least on one surface of the metal plate is preferably applied particularly to the outer plate parts of car bodies
25 and electric appliances.

Specific examples in the case where it is applied to the outer plate parts of car bodies include a method in which the conductive coated metal plate is cut, molded and, if necessary, joined to form a shell body for a car body and then a conductive plastic-coated
30 face, a cut end face and a metal-exposed part in this shell body are coated by electrodeposition coating to obtain a car body (hereinafter

called a method A); and a method in which the conductive coated metal plate is cut, molded and, if necessary, joined to form a car part and then this part is mounted on a main body of an automobile which has been assembled in advance to prepare a shell body, followed by coating a conductive plastic-coated face, a cut end face and a metal-exposed part in this shell body by deposition coating to obtain a car body (hereinafter called a method B).

In the method A described above, the conductive coated metal plate produced in the manner described above is cut, molded and joined to assemble a shell body. To be specific, the conductive coated metal plate is used to produce the respective parts for a main body and an outer covered part, and then they are combined to form a shell body.

This shell body is a part to which equipments such as an engine and a chassis are not installed and which is composed mainly of sheet metal. Among them, the main body is composed mainly of parts such as an underbody, a side member, a roof, a cowl, an upper back and a lower back. An outer covered part other than them is composed mainly of parts such as a hood, a front balance, a front fender, a cowl louver, doors and a luggage (back doors), and the respective parts in the outer covered part are called automobile parts.

The underbody means floor parts such as a passenger compartment (cabin) and a luggage boot and is a general term for a front underbody, a front floor and a rear floor. The side member is to combine with a front body, a roof panel and an underbody to form a side face of a cabin and prevent bending and torsion of the vehicle. The cowl is a panel for connecting longitudinal and lateral pillars. The upper back is a panel for connecting right and left quarter panels (rear fenders) at a rear part of a car body to form an outside face of the car body.

In the method A described above, in order to form the respective parts described above for constituting a shell body, the conductive coated metal plate produced in such manner as described above is cut to an intended shape and size and molded by pressing by means of a press working machine and, if necessary, they are joined by adhering with an adhesive, welding and bolting to produce respective parts for a main body such as an underbody, a side member, a roof, a cowl, an upper back and a lower back; and respective parts (automobile parts) for an outer covered part such as a hood, a front balance, a front fender, a cowl louver, doors and a luggage. They can be cut, molded and joined by known methods. Next, the respective parts for the main body which have been formed in the manner described above using the conductive coated metal plate are combined and joined to form the main body, and then the respective parts (automobile parts) for the outer covered part such as a hood, a front balance, a front fender, a cowl louver, doors and a luggage are mounted thereon.

The shell body which has been assembled in the manner described above using the conductive coated metal plate is coated at least on an outside thereof with the plastic layer. An end face of the cut plastic-coated metal plate is exposed at a metal part. Further, a back side thereof is preferably coated with the plastic, but the metal part is exposed in a certain case. In the method A described above, these metal-exposed parts can be subjected to electrodeposition coating.

On the other hand, in the method B described above, the conductive coated metal plate produced in the manner described above is used, and it is cut, molded and joined to produce the respective parts (automobile parts) for the outer covered part such as a hood, a front balance, a front fender, a cowl louver, doors and a luggage. These automobile parts are mounted on the main body of a

car body which has been assembled in advance to form a shell body. Among them, the respective parts (automobile parts) for the outer covered part for which the conductive coated metal plate is used can be produced in the same manner as in the method A.

5 In the method B described above, a great part or all of the automobile parts constituting the outer covered part are produced using the plastic-coated metal plate described above. For example, in order to form the respective parts such as a hood, a front balance, a front fender, a cowl louver, doors and a luggage (back doors) which
10 constitute the outer covered part, the plastic-coated metal plate is cut to an intended shape and size and molded by pressing by means of a press working machine and, if necessary, they are jointed by adhering with an adhesive, welding and bolting to produce the respective parts (automobile parts) such as a hood, a front balance
15 and the like. These cutting, molding and joining can be carried out by known methods. The respective parts (automobile parts) for the outer covered part which are molded in the manner described above are coated at least on the outsides thereof with the plastic layers, and the end faces of the cut steel sheets are exposed at metal parts.
20 Further, the back sides thereof may be exposed at metal parts without being coated or coated with the plastic.

 In the method B described above, the main body which is composed of an underbody, a side member, a roof, a cowl, an upper back and a lower back and on which these automobile parts are
25 mounted is produced usually by cutting, molding and working a non-coated metal plate without using a conductive coated metal and joining them by known methods. The respective parts (automobile parts) for the outer covered part which are produced using the conductive coated metal plate are mounted on the main body pro-
30 duced using such non-coated metal plate to prepare a shell body. In the method B described above, the whole surface of the main body in

the shell body which has been assembled in the manner described above and the metal-exposed parts of the the outer covered part (automobile parts) can be subjected to electrodeposition coating.

The electrodeposition paint used for obtaining the coated
5 metal plate of the present invention may be either an anionic type or a cationic type. In general, cationic type electrodeposition paint capable of forming a coated film having an excellent corrosion resistance is preferably used.

In the present invention, an electrodeposition coated film
10 is formed on the surface and the metal-exposed part of the conductive plastic coated film of the coated metal plate, and therefore preferably used is cationic electrodeposition paint having functions of an intermediate paint film such as a flatness, a ground covering property (covering fine irregularities on a coated surface to finish it
15 to the flat surface) and a weatherability in addition to functions of a conventional undercoated film (for example, a corrosion resistance, an adhesive property and a chipping resistance).

The cationic electrodeposition paint having both of such functions includes paints containing as a base resin, base resins
20 having a hydroxyl group and an amino group which can be converted to cation: for example, (i) cationic electrodeposition paints containing polyester resins, acryl resins and polyurethane resins each having a hydroxyl group and an amino group (see U.S. Patent No. 5,483,012); (ii) cationic electrodeposition paints containing amino group-contain-
25 ing epoxy resins which are modified by base resins such as polyester resins, acryl resins and polyurethane resins each having a hydroxyl group and an amino group (see U.S. Patent No. 5,739,185); and (iii) cationic electrodeposition paints containing as base resins, mixtures of nonionic resins such as polyester resins, acryl resins, modified
30 polyolefin resins and polyurethane resins with hydroxyl group and amino group-containing epoxy resins (see U.S. Patent Nos. 5,739,185

and 4,916,019; Japanese Laid-Open Patent Publication No. 292295/1995). These resins have preferably a number average molecular weight falling in a range of usually 400 to 10000, particularly 1000 to 4000. An amino group can be introduced into the resins, for example, by reacting resins having a functional group (for example, an epoxy group) capable of reacting with an amino group with primary or polyamines or secondary or polyamines, or using amino group-containing polymerizable monomers in producing the resins. The base resins thus obtained have an amine value falling preferably in a range of usually 3 to 200 mg/KOH, particularly 10 to 80 mg/KOH and a hydroxyl value falling preferably in a range of usually 10 to 200 mg/KOH, particularly 30 to 150 mg/KOH.

These cationic electrodeposition paints may be either an external cross-linking type using a curing agent in combination or an internal (self) cross-linking type in which a cross-linking functional group is coexistent in a base resin. The curing agent used in the form of an external cross-linking type includes, for example, block polyisocyanate compounds capable of reacting with a hydroxyl group and/or a primary or secondary amino group, amino resins and tri-(alkoxycarbonyl)triazines (common name: TACT). Among them, aliphatic block polyisocyanate compounds are particularly suited. Also, the cross-linking functional group of an internal (self) cross-linking type includes suitably, for example, a block isocyanate group and an α,β -unsaturated carbonyl group.

In the aliphatic block polyisocyanate compounds described above, substantially all isocyanate groups of the aliphatic polyisocyanate compounds are blocked with a volatile blocking agent, and if they are heated to a prescribed temperature or higher, this blocking agent is dissociated to regenerate the isocyanate groups, and they take part in a cross linking reaction with a base resin.

The aliphatic polyisocyanate compounds have two or more

free isocyanate groups in a molecule and include, for example, aliphatic diisocyanates such as hexamethylenediisocyanate, trimethylenediisocyanate, tetramethylenediisocyanate, dimer acid diisocyanate and lysine diisocyanate; and alicyclic diisocyanates such as isophoronediiisocyanate, methylenebis(cyclohexylisocyanate), methylcyclohexanediisocyanate, cyclohexanediisocyanate and cyclopentanediiisocyanate.

Further, the blocking agent which can be used for blocking the free isocyanate groups of these polyisocyanate compounds includes known blocking agents of a phenol base, an alcohol base, an active methylene base, a mercaptan base, an acid amide base, an imide base, an amine base, an imidazole base, a urea base, a carbamic acid base, an imine base, an oxime base, a sulfurous acid base and a lactam base.

A structural proportion of the base resin to the block polyisocyanate compound is 40 to 90 %, particularly 50 to 80 % for the former and 60 to 10 %, particularly 50 to 20 % for the latter each based on the total solid weight of both components.

The cationic electrodeposition paint can be prepared by blending the base resin, if necessary, with the curing agent such as a block polyisocyanate compound, then neutralizing a cationic group such as an amino group contained in the base resin with an acid compound such as acetic acid, formic acid, lactic acid, phosphoric acid and amidosulfonic acid and mixing with water. The pH in coating is controlled preferably in a range of usually 3 to 9, particularly 5 to 7, and the solid concentration is controlled preferably in a range of usually 5 to 30 % by weight.

The cationic electrodeposition paint can suitably be compounded, if necessary, with a curing catalyst having a corrosion resistance such as hydroxides, oxides, organic acid salts and inorganic acid salts of metals selected from, for example, aluminum,

nickel, zinc, strontium, lead, zirconium, molybdenum, tin, antimony, lanthanum, tungsten and bismuth; rust preventive pigments, color pigments usually used as an inhibitor, organic pigments, extender pigments and precipitation preventive.

5 The conductive coated metal plate is worked into an intended shape, molded, joined and then dipped in a cationic electrodeposition paint bath to be coated by electrodeposition at a bath temperature of 20 to 35°C, a voltage of 100 to 400 V and a current flow time of 1 to 10 minutes with this plate used as a cathode, where-
10 by electrodeposition coated films can be deposited on the surface of the conductive plastic film, the metal-exposed parts of the end faces brought about by cutting and the metal parts which are not coated with the plastics. These deposited electrodeposition coated films have a film thickness falling preferably in a range of usually about
15 10 to about 40 μm , particularly 10 to 20 μm in terms of a cured coated film thickness. After coating, the metal plate is drawn up from the paint bath, suitably washed with water and then heated at 100 to 200°C to cure electrodeposition coated films, whereby the coated metal plate intended by the present invention can be ob-
20 tained.

 In the coated metal plate which is coated by electrodeposition obtained according to the present invention, the electrodeposition coated film has a function as an intermediate coated film, so that intermediate coating which has so far been carried out can be
25 omitted and topcoat paint can be applied directly on the electrodeposition coated film surface, but conventional intermediate paint may be coated.

 According to the coated metal plate of the present invention described above, effects described below can be obtained.

30 (1) The metal plate is coated directly with the plastic and therefore improved notably in a chipping resistance as compared

with that of a composite coated film produced by electrodeposition coating-intermediate coating-top coating.

(2) Intermediate coating can be omitted, so that the coating steps can be shortened and the amount of VOC (volatile organic compounds) can be reduced to a large extent.

(3) The electrodeposition coated film which is coated on a plastic-coated surface has an excellent flatness, and therefore the surface of a top coated film formed thereon is improved as well in a flatness and a distinctness-of-image gloss.

10

EXAMPLES

The present invention shall more specifically be explained below with reference to examples and comparative examples. Both parts and percentage are based on weight, and the film thickness of a coated film is that of a cured coated film.

1. Production of conductive coated metal plate

(a) Used was a biaxial oriented polyester film (thickness: 16 μm) in which indium tin oxide (ITO) and palladium (Pd) were deposited on one surface thereof by sputtering, and a non-deposited surface thereof was subjected to corona discharge treatment. Then, a thermosetting polyester resin base adhesive was applied on this surface subjected to corona discharge treatment to a film thickness of 7 μm and heated at 120°C for 30 seconds. The deposited surface of the conductive film thus obtained had a surface resistance value of 10 Ω/\square .

Then, an alloyed molten zinc-plated steel sheet having a thickness of 0.8 mm and a plated deposition amount of 45 g/m² was subjected to degreasing and zinc phosphate treatment (trade name: "PB #3080" manufactured by Nihon Parkerizing Company). The conductive film described above was stuck on one face of this steel

30

sheet so that the adhesive layer of the conductive film contacted it and coated thereon by heat-pressing "conductive coated metal plate (a)".

(b) Used was a conductive polyester film with a thickness of 20 μm containing 30 % of furnace carbon black (conductive substance), and both faces thereof were subjected to corona discharge treatment. Then, a thermosetting polyester resin base adhesive containing 20 % of furnace carbon black was applied on one surface thereof to a film thickness of 7 μm and heated at 120°C for 30 seconds. The conductive film thus obtained had a volume specific resistance value of 30 $\Omega \cdot \text{cm}$.

Then, an alloyed molten zinc-plated steel sheet having a thickness of 0.8 mm and a plated deposition amount of 45 g/m^2 was subjected to degreasing and zinc phosphate treatment (trade name: "PB #3080" manufactured by Nihon Parkerizing Company). The conductive film described above was stuck on one face of this steel sheet so that the adhesive layer of the conductive film contacted it and coated thereon by heat-pressing "conductive coated metal plate (b)".

20

2. Examples and comparative examples

Example 1

The conductive coated metal plate (a) which was cut to a size of 15 cm \times 10 cm was dipped in a bath of a cationic electrodeposition paint (remark 1) and coated by electrodeposition on the conditions of a bath temperature of 28°C, a voltage of 250 V and a current flow time of 3 minutes with a metal-exposed part thereof used as a cathode, and then after drawing up from the bath and washing with water, it was heated at 170°C for 30 minutes to cure electrodeposition coated films. Formed were an electrodeposition coated film of 20 μm on the surface of the conductive film of the metal plate (a) thus

30

coated by electrodeposition, an electrodeposition coated film of 10 μm on the metal part of the end face and an electrodeposition coated film of 25 μm on the metal-exposed face of the back face.

Cationic electrodeposition paint (remark 1):

5 A flask equipped with a stirrer, a thermometer, a nitrogen-introducing tube and a reflux condenser was charged with 666 g of isophoronediiisocyanate (manufactured by DAICEL-Hülls Co., Ltd.), 269 g of methyl isobutyl ketone, 118 g of ethylene glycol monobutyl ether and 0.2 part of dibutyl tin dilaurate, and they were
10 reacted at 70°C under a nitrogen atmosphere until the concentration of an isocyanate group became 6.38 millimole/g. Then, 1634 g of Praxel 208 (OH equivalent: 409, manufactured by DAICEL CHEMICAL INDUSTRIES, LTD.) which was cyclic lactone ring-opened polyesterpolyol and reacted at 70°C under nitrogen atmosphere until
15 the concentration of an isocyanate group became 0.414 millimole/g to obtain a viscous urethane prepolymer.

Then, a flask equipped with a stirrer, a thermometer, a nitrogen-introducing tube and a reflux condenser was charged with 775 g of bisphenol A diglycidyl ether having an epoxy equivalent of
20 190, 237 g of bisphenol A and 13.5 g of methylbenzylamine, and they were reacted at 110°C until the epoxy concentration became 1.85 millimole/g to obtain an epoxy resin (a number average molecular weight: 1025 and an epoxy equivalent: 539). Added to this epoxy resin was 1333 g of the urethane prepolymer solution described
25 above, and they were reacted at 90°C until the isocyanate group was not detected. Then, the solution was diluted with 378 g of ethylene glycol monobutyl ether, and 200 g of diethanolamine was added and reacted at 90°C until the epoxy group was not detected. Then, the solution was diluted with ethylene glycol monobutyl ether to a solid
30 content of 75 % to obtain a polyurethane-modified amine-added epoxy resin having a primary hydroxyl group equivalent of 638 and

an amine value of 46.3.

On the other hand, 26 parts of butyl cellosolve was heated to 130°C, and 37.5 parts of a 80 % polyester monomer (trade name: "FM-3X", manufactured by DAICEL CHEMICAL INDUSTRIES, LTD.), 40 parts of styrene, 25 parts of hydroxyethyl methacrylate, 5 parts of n-butyl methacrylate and 4 parts of AIBN (azobisisobutyronitrile) were dropwise added thereto at the same temperature in 5 hours. Then, the solution was maintained at 130°C for 2 hours, and 5 parts of butyl cellosolve and 0.5 part of azobisdimethylvaleronitrile were dropwise added thereto at 130°C in 2 hours. Further, the solution was maintained at 130°C for 2 hours, and then 23 parts of cellosolve was added, followed by cooling down, whereby an acryl base resin solution having a solid content of 62 % and a number average molecular weight of about 5000 was obtained.

Mixed were 67 parts (solid) of the polyurethane-modified amine-added epoxy resin described above, 8 parts (solid) of the acryl base resin solution and 25 parts (solid) of methyl ethyl ketone oxime block isophoronediiisocyanate, and further added thereto were 1 g of polypropylene glycol (SANIX PP4000 manufactured by SANYO CHEMICAL INDUSTRIES, LTD.), 0.82 g of formic acid and 1 g of lead acetate each per 100 g of the resin solid. The solution was heated up to 40°C, and deionized water was slowly added thereto while stirring to prepare an aqueous dispersion, whereby a stable emulsion having a resin solid content of 30 % was obtained. Added were 3 g of basic lead silicate, 13 g of titanium white, 0.3 g of carbon, 3 g of clay, 2 g of dibutyl tin oxide and 1 g of a nonionic surfactant (trade name: "Noigen EA-142B" manufactured by DAI-ICHI KOGYO SEIYAKU CO., LTD.) each per 100 g of the resin solid of the emulsion thus obtained. The pigment was dispersed by means of a ball mill until the particle size thereof became 10 micron or less, and then the emulsion was further diluted with deionized water to a

resin solid content of 15 % to obtain a cationic electrodeposition paint.

Example 2

The conductive coated metal plate (b) having a thickness
5 of 0.8 mm which was cut to a size of 15 cm \times 10 cm was dipped in a
bath of the same cationic electrodeposition paint as in Example 1
and coated by electrodeposition on the conditions of a bath tempera-
ture of 28°C, a voltage of 250 V and a current flow time of 3 minutes
with a metal-exposed part thereof used as a cathode, and then after
10 drawing up from the bath and washing with water, it was heated at
170°C for 30 minutes to cure electrodeposition paint films. Formed
were an electrodeposition coated film of 20 μ m on the surface of the
conductive film of the metal plate (b) thus coated by electrodeposi-
tion, an electrodeposition coated film of 10 μ m on the metal part of
15 the end face and an electrodeposition coated film of 25 μ m on the
metal-exposed face of the back face.

Example 3

The conductive coated metal plate (a) having a thickness
of 0.8 mm which was cut to a size of 15 cm \times 10 cm was dipped in a
20 bath of the same cationic electrodeposition paint as in Example 1
and coated by electrodeposition on the conditions of a bath tempera-
ture of 28°C, a voltage of 300 V and a current flow time of 3 minutes
with a metal-exposed part thereof used as a cathode, and then after
drawing up from the bath and washing with water, it was heated at
25 170°C for 30 minutes to cure electrodeposition coated films. Formed
were an electrodeposition coated film of 35 μ m on the surface of the
conductive film of the metal plate (a) thus coated by electrodeposi-
tion, an electrodeposition coated film of 15 μ m on the metal part of
the end face and an electrodeposition coated film of 40 μ m on the
30 metal-exposed face of the back face.

Example 4

A non-coated metal plate having a thickness of 0.8 mm was cut, molded and joined to prepare in advance a model (about one-twenty fifth as large as the actual article in size) of a main body comprising an underbody, a side member, a roof, a cowl, an upper back and a lower back. On the other hand, the conductive coated metal plate (a) was cut, molded and joined to prepare models (about one-twenty fifth as large as the actual articles in size) of outer covered parts (automobile parts) such as hoods, fenders, doors and luggage doors.

These outer covered parts were mounted on the main body described above to form a shell body, and this was dipped in a bath of the same cationic electrodeposition paint as in Example 1 and coated by electrodeposition on the conditions of a bath temperature of 28°C, a voltage of 250 V and a current flow time of 3 minutes, and then after washing with water, it was heated at 170°C for 30 minutes to cure electrodeposition coated films. Formed were an electrodeposition coated film of 20 μm on the surface of the conductive film of the shell body thus coated by electrodeposition, an electrodeposition coated film of 10 μm on the metal part of the end face and an electrodeposition coated film of 25 μm on the metal-exposed face of the back face.

Example 5

The same operation as in Example 4 was carried out, except that the conductive coated metal plate (a) used in Example 4 was changed to the conductive coated metal plate (b).

Comparative Example 1

Electrodeposition coating was carried out in the same manner as in Example 1, except that the conductive coated metal plate (a) used in Example 1 described above was changed to a non-coated metal plate which was subjected to alloyed molten zinc plat-

ing so that the plated deposition amount became 45 g/m^2 and then to degreasing treatment and zinc phosphate chemical conversion treatment ("PB #3080 treatment").

Comparative Example 2

- 5 The conductive coated metal plate (b) which was cut to a size of $15 \text{ cm} \times 10 \text{ cm}$.

3. Performance test results

- 10 The electrodeposition coated articles obtained in the examples and the comparative examples were subjected to the performance tests. The results thereof are shown in Table 1.

The test methods are as follows:

Chipping resistance:

A white topcoat paint (trade name: "AMILAC WHITE" manufactured by Kansai Paint Co., Ltd., polyester resin-melamine resin base) was applied to a film thickness of 35 μm on the coated metal plates obtained after electrodeposition coating - curing by heating in Examples 1 to 3 and Comparative Examples 1 to 2 and cured by heating at 140°C for 30 minutes. The coated plates thus obtained were tested.

A tester (trade name: "Q-G-R Gravelo Meter" manufactured by Q Panel Co., Ltd.) was used, wherein 50 g of No. 7 crushed stones was blown onto the coated surfaces at an air pressure of about 4 kg/cm^2 and an angle of 90 degree at -20°C; then, an adhesive cellophane tapes were stuck on the coated surfaces, and they were quickly peeled off; and then, the state of the coated films peeled off from the impacted parts was visually observed. A mark ○ shows that a little peeling of the top coated film caused by impact is observed but no exposure on the metal face is found; a mark △ shows that a lot of peeling of the top coated film caused by impact is observed and a little exposure on the metal face is found as well; and a mark × shows that a lot of peeling of the top coated film caused by impact is observed and a lot of exposure on the metal face is found as well.

Corrosion resistance for general parts:

The coated articles obtained in Examples 1 to 5 and Comparative Examples 1 to 2 were stored in a brine-resistance spray tester (35°C) for 960 hours, and then visually observed were the corrosion resistances at the conductive film-adhered parts (examples of the coated articles and the electrodeposition coated parts (comparative examples). A mark ○ shows that no rust and blister are observed to be produced; a mark △ shows that a little rust and

blister are observed to be produced; and a mark \times shows that a lot of rust and blister are observed to be produced.

Corrosion resistance for edges:

- The coated articles obtained in Examples 1 to 5 and
- 5 Comparative Examples 1 to 2 were stored in the brine-resistance spray tester for 240 hours, and then visually observed were the corrosion resistances at the end parts (acute angle parts) of the cut parts in the metal plates. A mark \bigcirc shows that no rust is observed to be produced at the end part; a mark \triangle shows that a little rust is
- 10 observed to be produced at the end part; and a mark \times shows that a lot of rust is observed to be produced at the end part.

Clarity:

- An image clarity measuring apparatus (trade name: "IMAGE CLARITY METER" manufactured by SUGA TEST INSTRUMENT CO., LTD.) was used to measure a clarity on the top
- 15 coated surface. A white topcoat paint ("AMILAC WHITE ") was applied to a film thickness of 35 μm on the coated metal plates obtained in Examples 1 to 5 and Comparative Examples 1 to 2 and cured by heating at 140°C for 30 minutes. The coated plates thus
- 20 obtained were measured for a clarity on the top coated surface. The numerals in the table are values falling in a range of 0 to 100 % in terms of an ICM value, and it is shown that the larger the value is, the more excellent the clarity is. The ICM value of 80 or more shows that the clarity is very good.

25 Weatherability:

- A top clear (trade name: "MAGICRON CLEAR #7000" manufactured by Kansai Paint Co., Ltd.) was applied on the coated articles obtained in Examples 1 to 5 and Comparative Examples 1 to 2 and cured by heating. Repeated for the test plates thus obtained
- 30 was a cycle of storing in a sunshine weather meter (test temperature: 63 \pm 3°C, spray period: 12 minutes in 60 minutes and humidity:

50 \pm 5 %) for 20 hours and dipping in warm water of 40°C for 2 hours. After finishing each cycle, crosscuts were put on the coated plates, and the peeling property with a cellophane adhesive tape was observed to evaluate the adhesive property. The case where peeling
5 was caused in a wide range in the circumference of the crosscuts on the coated films was marked with \times , and the test time (unit: hour) spent until peeling reached the state of \times was determined.

CLAIMS:

1. A coated metal plate characterized by comprising a metal plate and laminated at least on one surface of a metal plate, a conductive plastic coated film and an electrodeposition coated film.
2. The coated metal plate as described in claim 1, wherein the plastic coated film is obtained by adhering a film- or sheet-shaped plastic on the metal plate.
3. The coated metal plate as described in claim 1, wherein the plastic coated film has a thickness falling in a range of 1 to 100 μm , particularly 3 to 75 μm .
4. The coated metal plate as described in claim 1, wherein the conductive plastic coated film contains a conductive substance in the plastic coated film and has a volume specific resistance value of $10^3 \Omega \cdot \text{cm}$ or less.
5. The coated metal plate as described in claim 1, wherein the conductive plastic coated film has a conductive layer on the surface of the plastic coated film and has a surface resistance value of $100 \Omega/\square$ or less.
6. The coated metal plate as described in claim 1, wherein the electrodeposition coated film is a coated film formed from a cationic type electrodeposition paint.
7. The coated metal plate as described in claim 6, wherein the cationic electrodeposition paint contains a base resin having a hydroxyl group and an amino group which can be converted to cation and an aliphatic block polyisocyanate compound.
8. The coated metal plate as described in claim 1, wherein the electrodeposition coated film has a thickness falling in a range of about 10 to about 40 μm , particularly 10 to 20 μm .
9. A car body using the coated metal plate as described in claim 1.

Abstract of the Disclosure

According to the present invention, provided is a coated metal plate characterized by comprising a metal plate and laminated at least on one surface of a metal plate, a conductive plastic coated film and an electrodeposition coated film, which is useful as an outer plate part for car bodies and electrical appliances.

DECLARATION AND POWER OF ATTORNEY FOR U.S. PATENT APPLICATION

(X) Original () Supplemental () Substitute () PCT () Design

As a below named inventor, I hereby declare that: my residence, post office address and citizenship are as stated below next to my name; that I verily believe that I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural inventors are named below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

Title: COATED METAL PLATE

of which is described and claimed in:

- (X) the attached specification, or
 () the specification in the application Serial No. _____ filed _____;
 and with amendments through _____ (if applicable), or
 () the specification in International Application No. PCT/ _____, filed _____, and as amended
 on _____ (if applicable).

I hereby state that I have reviewed and understand the content of the above-identified specification, including the claims, as amended by any amendment(s) referred to above.

I acknowledge my duty to disclose to the Patent and Trademark Office all information known to me to be material to patentability as defined in Title 37, Code of Federal Regulations, §1.56.

I hereby claim priority benefits under Title 35, United States Code, §119 (and §172 if this application is for a Design) of any application(s) for patent or inventor's certificate listed below and have also identified below any application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

COUNTRY	APPLICATION NO.	DATE OF FILING	PRIORITY CLAIMED
Japan	359,021/98	December 17, 1998	Yes

I hereby claim the benefit under Title 35, United States Code, §120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge the duty to disclose information material to patentability as defined in Title 37, Code of Federal Regulations, §1.56 which occurred between the filing date of the prior application and the national or PCT international filing date of this application.

APPLICATION SERIAL NO.	U.S. FILING DATE	STATUS: PATENTED, PENDING, ABANDONED

And I hereby appoint John T. Miller, Reg. No. 21,120; Michael R. Davis, Reg. No. 25,134; Matthew M. Jacob, Reg. No. 25,154; Jeffrey Noltan, Reg. No. 25,408; Warren M. Cheek, Jr., Reg. No. 33,367; Nils E. Pedersen, Reg. No. 33,145 and Charles R. Watts, Reg. No. 33,142, who together constitute the firm of WENDEROTH, LIND & PONACK, L.L.P., attorneys to prosecute this application and to transact all business in the U.S. Patent and Trademark Office connected therewith.

I hereby authorize the U.S. attorneys named herein to accept and follow instructions from ODAJIMA & CO. as to any action to be taken in the U.S. Patent and Trademark Office regarding this application without direct communication between the U.S. attorneys and myself. In the event of a change in the persons from whom instructions may be taken, the U.S. attorneys named herein will be so notified by me.

Send Correspondence to

WENDEROTH, LIND & PONACK, L.L.P.
2033 K Street, N.W., Suite 800
Washington, DC 20006

Direct Telephone Calls to:

WENDEROTH, LIND & PONACK, L.L.P.
Area Code (202) 721-8200

Direct Facsimile Messages to:

Area Code (202) 721-8250

Full Name of First Inventor	FAMILY NAME WATANABE	FIRST GIVEN NAME Tadashi	SECOND GIVEN NAME
Residence & Citizenship	CITY Hiratsuka-shi	STATE OR COUNTRY Kanagawa-ken	COUNTRY OF CITIZENSHIP Japan
Post Office Address	ADDRESS 33-23, Hanamizudai, Hiratsuka-shi,	CITY Kanagawa-ken,	STATE OR COUNTRY Japan
Full Name of Second Inventor	FAMILY NAME HIRAKI	FIRST GIVEN NAME Tadayoshi	SECOND GIVEN NAME
Residence & Citizenship	CITY Odawara-shi	STATE OR COUNTRY Kanagawa-ken	COUNTRY OF CITIZENSHIP Japan
Post Office Address	ADDRESS 240-20, Nakamurahara, Odawara-shi,	CITY Kanagawa-ken,	STATE OR COUNTRY Japan
Full Name of Third Inventor	FAMILY NAME TOMINAGA	FIRST GIVEN NAME Akira	SECOND GIVEN NAME
Residence & Citizenship	CITY Chigasaki-shi	STATE OR COUNTRY Kanagawa-ken	COUNTRY OF CITIZENSHIP Japan
Post Office Address	ADDRESS 22-18, Matsukazedai, Chigasaki-shi,	CITY Kanagawa-ken,	STATE OR COUNTRY Japan
Full Name of Fourth Inventor	FAMILY NAME YAWATA	FIRST GIVEN NAME Takeshi	SECOND GIVEN NAME
Residence & Citizenship	CITY Hiratsuka-shi	STATE OR COUNTRY Kanagawa-ken	COUNTRY OF CITIZENSHIP Japan
Post Office Address	ADDRESS 4-13-12, Higashiyawata,	CITY Hiratsuka-shi,	STATE OR COUNTRY Kanagawa-ken, Japan

Full Name of Fifth Inventor	FAMILY NAME	FIRST GIVEN NAME	SECOND GIVEN NAME
Residence & Citizenship	CITY	STATE OR COUNTRY	COUNTRY OF CITIZENSHIP
Post Office Address	ADDRESS	CITY	STATE OR COUNTRY ZIP CODE

Full Name of Sixth Inventor	FAMILY NAME	FIRST GIVEN NAME	SECOND GIVEN NAME
Residence & Citizenship	CITY	STATE OR COUNTRY	COUNTRY OF CITIZENSHIP
Post Office Address	ADDRESS	CITY	STATE OR COUNTRY ZIP CODE

Full Name of Seventh Inventor	FAMILY NAME	FIRST GIVEN NAME	SECOND GIVEN NAME
Residence & Citizenship	CITY	STATE OR COUNTRY	COUNTRY OF CITIZENSHIP
Post Office Address	ADDRESS	CITY	STATE OR COUNTRY ZIP CODE

I further declare that all statements made herein of my own knowledge are true, and that all statements on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

1st Inventor Tadashi Watanabe Date December 10, 1999
 2nd Inventor Tadayoshi Hiraki Date December 10, 1999
 3rd Inventor Akira Tomimaga Date December 10, 1999
 4th Inventor Takeshi Sawata Date December 10, 1999
 5th Inventor _____ Date _____
 6th Inventor _____ Date _____
 7th Inventor _____ Date _____

The above application may be more particularly identified as follows:

U.S. Application Serial No. _____ Filing Date _____
 Applicant Reference Number _____ Atty Docket No. _____
 Title of Invention _____
